

Please amend the Application as follows.

IN THE CLAIMS:

1. (Cancelled)

2. (Cancelled)

3. (Currently Amended): Moulding composition according to claim 10, containing 1 to 18 parts by weight of phosphorus compound (I) or a mixture of phosphorus compounds (I).

4. (Currently Amended): Moulding composition according to claim 10, containing 2 to 16 parts by weight of phosphorus compound (I) or a mixture of phosphorus compounds (I).

5. (Cancelled)

6. (Cancelled)

7. (Cancelled)

8. (Currently Amended): Moulding composition according to claim ~~7~~ 10, containing 1 to 40 parts by weight of graft polymer.

9. (Currently Amended): Moulding composition according to Claim ~~7~~ 10 wherein ~~the graft polymer is prepared by copolymerization of:~~

(B.1) ~~5 to 95 parts by weight of~~ comprises a mixture of,

(B.1.1) 50 to 95 parts by weight of styrene, α -methylstyrene, halo- or alkyl-ring-substituted styrene, C₁-C₈ alkyl methacrylate, C₁-C₈ alkyl acrylate or mixtures of these compounds, and

(B.1.2) 5 to 50 parts by weight of acrylonitrile, methacrylonitrile, C₁-C₈ alkyl methacrylate, C₁-C₈ alkyl acrylate, maleic anhydride, C₁-C₄ alkyl- or phenyl-N-substituted maleimide or mixtures of these compounds; and

~~(B.2) 5 to 95 parts by weight of rubber having a glass transition temperature of below 10°C.~~

10. (Currently Amended): ~~A Moulding~~ moulding composition according to ~~Claim 1 containing~~ consisting of:


A) 40 to 99 parts by weight of at least one of aromatic polycarbonate and polyester-carbonate selected from at least one member of the group consisting of bisphenol A homopolycarbonates and copolycarbonates of bisphenol A and up to 15 mol% of at least one other diphenol;

B) 0.5 to 60 parts by weight of graft polymer prepared from the copolymerization of,

B.1) 5 to 95 wt.% of one or more vinyl monomers, and

B.2) 95 to 5 wt.% of one or more grafting backbones having a glass transition temperature of <10°C, said grafting backbone having an average particle size of 0.10 to 0.6 μ m, and a gel content of at least 40 wt.%;

- C) 0 to 45 parts by weight of at least one thermoplastic polymer selected from vinyl (co)polymers and polyalkylene terephthalates;
- D) 0.5 to 20 parts by weight of said phosphorus compound represented by formula (I),



in which

R^1 , R^2 , R^3 and R^4 are mutually independently C_1 - C_8 alkyl, optionally substituted by halogen, C_5 - C_6 cycloalkyl, C_6 - C_{10} aryl or C_7 - C_{12} aralkyl, each optionally substituted by halogen and/or alkyl,

n mutually independently mean 0 or 1,

q mutually independently mean 0, 1, 2, 3 or 4,

N means 0.9 to 2.5,

R^5 and R^6 mutually independently mean C_1 - C_4 alkyl or halogen,

Y means C_1 - C_7 alkylidene, C_1 - C_7 alkylene, C_5 - C_{12} cycloalkylene, C_5 - C_{12} cycloalkylidene, -O-, -S-, -SO-, -SO₂- or -CO-; and

- E) 0 to 3 parts by weight of fluorinated polyolefin; and

F) at least one additive selected from the group consisting of stabilisers, pigments, mould release agents, flow auxiliaries and antistatic agents.

11. (Currently Amended): Moulding compositions according to Claim 10 wherein Y in the formula (I) denotes isopropylidene or methylene.

12. (Currently Amended): Moulding compositions according to Claim 10 wherein grafting backbone B.2 comprises at least one of ~~containing a~~ diene rubber, acrylate rubber, silicone rubber ~~or~~ and ethylene/propylene/diene rubber ~~or mixtures thereof as the grafting backbone B.2.~~

13. (Cancelled)

14. (Currently Amended): A method of ~~using the~~ preparing a molded article comprising:

(a) providing the moulding compositions ~~according to~~ of Claim 10; ~~and for the production of mouldings.~~

(b) injection molding said molding composition to form said molded article.

15. (Currently Amended): Mouldings prepared from the moulding compositions according to Claim 10.

16. (New): The moulding composition of Claim 10 wherein N of formula (I) is 1 to 1.15.

17. (New): The moulding composition of Claim 10 wherein said other diphenol of said aromatic polycarbonate (A) is selected from hydroquinone, resorcinol, dihydroxydiphenols, bis-(hydroxyphenyl)-C₁-C₅-alkanes, bis-(hydroxyphenyl)-C₅-C₆-cycloalkanes, bis-(hydroxyphenyl) ethers, bis-(hydroxyphenyl) sulfoxides, bis-(hydroxyphenyl) ketones, bis-(hydroxyphenyl)

sulfones, α,α -bis-(hydroxyphenyl)diisopropylbenzenes, ring-brominated derivatives thereof and ring-chlorinated derivatives thereof.

18. (New): The moulding composition of Claim 10 wherein the other diphenol of said aromatic polycarbonate is 2,2-bis-(3,5-dibromo-4-hydroxyphenyl)propane.